

ISSN Print: 2664-6781 ISSN Online: 2664-679X IJACR 2023; 5(1): 106-109 www.chemistryjournals.net Received: 27-12-2022 Accepted: 04-02-2023

Shiv Prakash Mishra

Faculty of Science, Department of Chemistry, Dr. RMLA University, Ayodhya, Uttar Pradesh, India

RP Singh

Professor, Department of Chemistry, KNIPSS, Sultanpur, Uttar Pradesh, India

Corresponding Author: Shiv Prakash Mishra Faculty of Science, Department of Chemistry, Dr. RMLA University, Ayodhya, Uttar Pradesh, India

Substitution of dicarboxylate ions as succinate ion in 'Apatite World'

Shiv Prakash Mishra and RP Singh

DOI: https://doi.org/10.33545/26646781.2023.v5.i1b.149

Abstract

In crystal chemistry, the apatite crystals is prepared by the dissolution precipitation reaction, which led to HAP (hydroxyapatite; $Ca_{10}(PO_4)_{6.}(OH)_2$) Nano crystals formation under hydrothermal condition from OCP (Octacalcium phosphate; $Ca_8(HPO_4)_2.(PO_4)_4.5H_2O$) at 180 °C for 3 hours with adjusted 5.5 pH range. The prepared solution is incorporating to dicarboxylate as succinate (OOC (CH₂)₂.COO)²⁻ ions. During incorporating of succinate ions in OCP crystals, the hydrogen phosphate (HPO₄²⁻) ions in the hydrated layers of OCP are being substituted by succinate ions. These organically modified OCP which generated to HAP have unique hexagonal nanostructures with micrometer thickness are characterized by reporting of scanning electron microscopy (SEM), X-ray diffraction analysis, Fourier transform infrared (FTIR) spectra and Scherrer's equation as well.

Keywords: Succinate ion, octacalcium phosphate, hydroxyapatite, hydrogen phosphate, Scherrer's equation

1. Introduction

In chemistry of 'apatite world' the bio-apatite are indispensable for which the general formula is $Ca_5(PO_4)_3X$, where X=F, Cl or OH, since they are key component of bone and teeth. Recently, synthetic apatites that permit bone grafts are now available ^[1], but, a bone like nanocrystaline apatite have been formed via using self-assembled liquid crystals ^[2]. The hydroxyapatite (HAP; $Ca_{10}(PO_4)_6$.(OH)₂ which is the main inorganic components of hard tissue such as bone and teeth and they are used in medicinal applications have attracted a great attention including several applications such as artificial organs, tissue engineering, medical devices, and dentistry, etc ^[3]. Although, a NMR characteristic transformation behaviors of octacalcium phosphate (OCP; Ca₈(HPO₄)₂.(PO₄)₄.5H₂O) to HAP have been reported ^[4, 5], which is different from those of other calcium phosphate compounds under hydrothermal conditions (in vitro-vivo) [6-8]. The HAP can be synthesized from various calcium orthophosphates such as α - and β -tricalcium phosphate (TCP; Ca₃(PO₄)₂) and OCP as well ^[9]. For TCP, since HAP is generated by a dissolution precipitation reaction, there is no correlation between the crystal shape of the original TCP particle and the shape of the HAP particles generated. Generally, needle-shaped HAP crystals are formed from granular α - and β -TCP particles under hydrothermal conditions ^[10, 11]. Plate-shaped OCP crystals are transformed to laminated thin plate-shaped HAP Nanocrystals under hydrothermally and characterized the resultant HAP. The OCP crystal is composed of apatite and hydrated layers producing plate-shaped crystals [12, 13]. Where, the hydrogen phosphate ion (HPO₄²⁻) in the hydrated layers can be substituted or incorporated by dicarboxylate such as succinate ions into OCP crystal structure has been reported ^[14-17]. The molecular structure of succinic acid and its ion is shown in Figure 1.



Fig 1: The molecular structure of succinic acid (HOOC. (CH₂)₂.COOH) and succinate ion (OOC.(CH₂)₂.COO)²⁻

2. Experimental

In experimental procedure, a dicarboxylic acid such as succinic acid-based modified octacalcium phosphate (OCP; $Ca_8(HPO_4)_2.(PO_4)_4.5H_2O)$ in incorporated with succinate ion has been synthesized by a previously reported method ^[18, 19]. Here, the reported work is performed well by adapted from the work of as T. Yokoi et al. [20]. The required materials as chemicals and regents have been laboratory-based standard is used. In this method, 20 mmol of succinic acid (HOOC(CH₂)₂COOH); 99.5%, (Wako Pure Chemical Industries Ltd., Osaka, Japan) is dissolved in 200 cm³ of ultra-pure water, where the pH of solution is adjusted to 5.5 by adding an appropriate amount of ammonia solution (aqu.NH₃ soln.;25%). The 16.0 mmol of calcium carbonate (CaCO₃; calcite, Nacalai Tesque Inc., Kyoto, Japan) has been suspended in the dicorboxylic acid solution and 10.0 mmol of phosphoric acid (H₃PO₄; 85% Aqu. soln, Wako Pure Chemical Industries Ltd) is mixed with the suspension. Then suspension is stirred at 60°C, and after about 3h, the pH of the suspension is reduced to 5.0 by using 1.0 mol. dm⁻ ³ HCl solution and after 30 minutes, the precipitates has been isolated by vacuum filtration and gently rinsed with ultra-pure water and ethanol (C₂H₅OH), followed by drying overnight at 40 °C.

The sample which synthesized in solution containing 20 mmol of succinic acid is denoted as Suc-20 as well as OCP those not containing dicarboxylate ion is also synthesized by using 16.0 mmol of CaCO₃ and 12.0 mmol of H₃PO₄ which may denoted as Control or Calphos. Now, Calphos (0.10 g) and Suc-20(0.10 g) are added to a 28 cm³. Teflon vessel with 10 cm^3 of ultra-pure water. The samples have encapsulated in an autoclave, and then hydrothermally treated at 180 °C for 3 h. These hydrothermal treatment condition under which the phase transformation is completed in a short time may selected because as the reaction time become longer, the morphological differences in the morphology of generated hexagonal HAP due to different starting materials disappear due to aging, where hydrothermally treated sample has collected by vacuum filtration and it dried overnight at 40 °C, respectively.

The crystalline phases of the different hydroyapatite (Calphos or Control and Suc- or SUC 20) sample products have characterized by powder X-ray diffraction (XRD; RINT-2000, Rigaku Co., Tokyo, Japan) using Cu-K α

radiation. The chemical structures of the given samples have characterized by using of Fourier- transform infrared (FTIR) spectroscopy (Frontier MIR/NIR, Perkin-Elmer Japan Co., Ltd., Kanagawa, Japan) as using the KBr tablet method. The morphologies of the formed samples have been characterized by scanning electron microscopy (SEM; SU-8000, Hitachi, Ltd., Tokyo, Japan) as well.

3. Results and Discussion

In this paper we have effort and try to mention that, about the succinate incorporated OCP, although, following a procedure well reported ^[18]. The report reveals that the Ca/P molar ratio of OCP with incorporated or complexed succinate (SUC- or Suc-OCP) ion is expected to be 1.56± 0.02. The transformation of Suc-20 have proceeded under hydrothermal condition and Suc-OCP is completely transformed to HAP by hydrothermal treatment at 180°C for 3 hours. There is no by- products such as dicalcium phosphate anhydrous are detected by XRD analysis. It is reported that the colour of Suc-OCP changed from white to light brown upon heat treatment at 450 °C in an air due to residual corbon formation. Notable, the colour of both Control or Calphos and Suc-20 before and after hydrothermal treatment was white and none of the color may observed visually. Hence, succinate ion decomposition may not occur under the hydrothermal conditions. Here, in Figure 2 (a, and b) we have shown the XRD and SEM magnification image of OCP which are as starting materials for transformation reaction.



Fig 2: The XRD pattern (a), and (b) SEM image for OCP before hydrothermal treatment.



Fig 3: (A) - The XRD patterns of samples (CONTROL and SUC20) {under before (I), after (ii), and (B) - The SEM magnification images of sample under hydrothermally treatment at 180 °C for 3 hours, ^[20]

Indeed, the crystal morphology of the various samples (Calphos or Control, Suc-20, Suc-OCP and Pure-OCP) before and after hydrothermal treatment at 180 °C for 3

hours have been well assigned ^[19, 21]. Here, the Figure 3 (A) has shown the crystalline phases of the different products are being characterized by powder X-ray diffraction (XRD),

and, in Figure 3 (B) as scanning electron microscopy (SEM) observation of dark line at HAP crystal's center. The Figure 4 (A) indicated FTIR spectra with the absorption peak of HPO_4^{2-} located in the hydrated layer is detected at 1193 cm⁻¹, ^[22, 23]. This peak is not absorbed for Suc-20 because HPO_4^{2-} is replaced by the succinate ion. The observation peaks arising from the COO stretching and CH₂ bending modes of the complexated succinate ion are observed at

$5 Ca_{8} (HPO_{4}) _{2} (PO_{4})_{4} . 5H_{2}O \ 4 Ca_{10} (PO_{4})_{6} (OH)_{2} + 6 H_{3}PO_{4} + 17H_{2}O$

In transformation reaction of OCP to HAP Nano crystals under hydrothermal conditions as shown in equation 1, the pH of used solvent are 5.5 but its value may decrease in treatment conditions because of the formation of phosphoric acid (H₃PO₄). In crystal morphology of the samples before and after hydrothermal treatment at 180 °C for 3 hours have displayed that, both the as-synthesized and hydrothermally treated CALPHOS samples are composed of plate-shaped crystals several micrometers in size, although the crystalline phase is changed from OCP to hexagonal HAP. Therefore, for pure-OCP, the crystal morphology is almost retained after phase transformation ^[12, 13]. Similarly, to CALPHOS 1565, 1460 and 1300 cm⁻¹. After the hydrothermal treatment, the absorption peak corresponding to HAP are detected for both hydrothermally treated Calphos and Suc-20. Although, in some cases, hydrothermally synthesized HAP includes carbonate ions in its crystal lattice, the absorption peaks corresponding to the carbonate ion are not detected in our samples. In respect of crystalline phase the FTIR spectral observation are in line with XRD results.

(1)

there is no change in the macroscopic morphology for Suc-20. These findings strongly suggested that the phase transformation mechanism for Suc-OCP is similar to that of pure-OCP. On the basis of SEM images report of the different samples, we observed that, the HAP crystals, where the thickness of HAP crystals, formed by the hydrothermal treatment of CALPHOS is in range 50-150 nm similar to those of plate-shaped crystals before hydrothermal treatment. The present observation have shown the dark line are found at the centre of the Suc-20 crystal after hydrothermal treatment, which can attributed to the gap between two thin-plate crystals.



Fig 4: (A)- The FTIR spectra of samples Control and SUC20 under before (a), and after (b) hydrothermal treatment at 180 °C for 3 hours, and (B)- The D_{100} values of hydroxyapatite (HAP) prepared from, (a) Calphos and (b) Suc-20, calculated by using of Scherrer equation, ^[20].

Although, a survey reveals that the crystallite system for HAP is hexagonal, where the crystallite size in the direction of the various axes (a, b, c) dependent on the thickness of the plate-shaped HAP crystals ^[13, 20, 24, 25]. These crystallite size perpendicular to the (100) plane which are calculated by the using of Scherrer equation (as equation 2) to compare the thickness of the plate-shaped HAP crystal of CALPHOS and Suc-20 after hydrothermal treatment at 180 °C for 3 hours.

$$D100 = \mathbf{K} \,\lambda \,/\,(\beta \cos \theta) \tag{2}$$

Here, the *D*100 is the crystallite size perpendicular to (100) plane, K is Scherrer constant (=0.9), λ is the wavelength of incident X-ray (0.154 nm), β is the full width at half-maximum of the 100-reflection peak for HAP and θ is the diffraction angle. Figure 4 (B) show that the *D*100 values of samples as HAP synthesized from Suc-20 are smaller than those of HAP prepared from CALPHOS. Thus, calculation of crystallite size support as well as SEM agreement that, the presence of dark line corresponding to gap between too thin-plate crystals, therefore, the HAP crystal which are obtained from Suc-20 likely have laminated nanostructures. Where, the elimination of succinate ion from interlayer of

OCP crystal is necessary for the transformation from OCP with incorporated succinate ion to HAP. The laminated nanostructure is formed probably because the succinate ions inhibit crystal growth in the thickness direction.

4. Conclusion

In conclusion, we have reported the study of preparation and characterization of a hydroxyapatite (HAP) Nano crystals *via* hydrogen phosphate (HPO $_4^{2-}$) ions substitution in hydrated layers of octa-calcium phosphate (OCP) by dicarboxylate as succinate ions (OOC.CH₂-CH₂.COO)²⁻. These crystals are transformed through hydrothermal precipitation reaction at 180 °C for 3 hours with adjusted pH to 5.5 and incorporated to dicarboxylic (e.g. succinic) acid having Ca/P molar ratio expected to be 1.56±0.02. During incorporation of organically succinate ions into OCP crystal, the substitution of hydrogen phosphate (HPO₄²⁻) ions in hydrated layer of OCP are replaced by succinate ions. The crystalline size and thickness of generated hexagonally plate-shaped HAP are calculated by introducing of Scherrer's equation. The characteristic observation of produced hexagonally HAP Nano crystals have been studied by using of SEM, Fourier Transform Infrared (FTIR) and powder XRD technique as well.

5. Acknowledgement

Work supported by various respective Journals and books. The author gratefully acknowledge support of Faculty of Science, as well as Department of Physics & Electronics, Dr. Rammanohar Lohia Avadh University, Ayodhya-224001, (U.P.), India, for providing useful discussion and necessary facilities.

6. References

- Cotton FA, Wilkinson G, Murillo CA, Bochmann M. Textbook of Adv. Inorg. Chem., John Welly & Sons, Inc., 6th Edition; c1999.
- 2. He W, Kjellin P, Currie F, Handa P, Knee CS, Bielecki J, *et al.* Formation of bone-like nano crystalline apatite using self-assembled liquid crystals. Chemistry of Materials. 2012 Mar 13;24(5):892-902.
- 3. Dorozhkin SV, Epple M. Biological & Medical Significance of Calcium Phosphate, Angew. Chemie International Edition. 2002;41:3130-3146.
- 4. Tseng YH, Mou CY, Chan JCC. Solid-state NMR study of the transformation of octacalcium phosphate to hydroxyapatite: A mechanistic model for central dark line formation. Journal of the American Chemical Society. 2006;128(21):6909-6918.
- 5. Yoshimura M, Suda H, Okamaoto K, Ioku K. Hydrothermal Synthesis of Biocompatible Whiskers. Journal of Materials Science. 1994;29:3399-3402.
- 6. Crane JL, Cao X. Bone Marrow Mesenchymal Stem Cells and TGF-β signaling in Bone Remodeling. The Journal of Clinical Investigation. 2014;124(2):466-472.
- 7. Suzuki O, Imaizumi H, Kamakura S, Katagiri T. Bone Regeneration by Synthetic Octacalcium Phosphate and its Role in Biological Mineralization. Current Medicinal Chemistry. 2008;15(3):305-313.
- 8. Horvathova R, Muller L, Helebrant A, Greil P, Muller FA. *In vitro* Transformation of OCP into Carbonated HA under physiological conditions. Materials Science and Engineering: C. 2008;28(8):1414-1419.
- 9. Yu T, Zhang J, Zhu W. Chondrogenesis Mediates Progression of Ankylosing Spondylitis through Heterotopic Ossification. Bone Res. 2021 Mar 17;9(1):01-19.
- Ioku K, Kawachi G, Sasaki S, Fujimori H, Goto S. Hydrothermal Preparation of Tailored Hydroxyapatite. Journal of Materials Science. 2006 Mar;41:1341-1344.
- 11. Goto T, Kim IY, Kikuta K, Ohtsuki C. Comparative Study of hydroxyapatite formation from α and β -tricalcium phosphates under hydrothermal conditions. Journal of the Ceramic Society of Japan. 2012;120(1400):131-137.
- 12. Kamitakahara M, Ito N, Murakami S, Watanabe N, Ioku K. Hydrothermal Synthesis of Hydroxyapatite from Octacalcium Phosphate. Effect of Hydrothermal Temperature. Hydrothermal synthesis of hydroxyapatite from octacalcium phosphate: Effect of hydrothermal temperature. Journal of the Ceramic Society of Japan. 2009;117(1363):385-387.
- Ito N, Kamitakahara M, Murakami S, Watanabe N, Ioku K. Hydrothermal Synthesis and Characterization of Hydroxyapatite from Octacalcium Phosphate. Journal of the Ceramic Society of Japan. 2010;118(1380):762-766.
- 14. Yokoi T, Kato H, Kim IY, Kikuta K, Kamitakahara M, Kawashita M, et al. Formation of Octacalcium

Phosphates with co-incorporated succinate and suberate ions. Dalton Transactions. 2012;41(9):2732-7.

- 15. Yokoi T, Goto T, Kitaoka S. Transformation of Dicalcium Phosphate Dihydrate into Octacalcium Phosphate with Incorporated Dicarboxylate Ions. Journal of the Ceramic Society of Japan. 2018;126(6):462-468.
- Monma H, Goto M. Succinate-complexed Octacalcium Phosphate. Bulletin of the Chemical Society of Japan. 1983 Dec;56(12):3843-3844.
- Monma H. The incorporation of dicarboxylates into octacalcium bis (hydrogen phosphate) tetrakis (Phosphate) pentahydrate. Bulletin of the Chemical Society of Japan. 1984;57(2):599-600.
- Kamitakahara M, Okano H, Tanihara M, Ohtsuki C. Synthesis of octacalcium phosphate intercalated with dicarboxylate ions from calcium carbonate and phosphoric acid. Journal of the Ceramic Society of Japan. 2008;116(1351):481-485.
- 19. Yokoi T, Kato H, Kim IY, Kikuta K, Kawashita M, Ohtsuki C. Synthesis of octacalcium phosphate with incorporated succinate and suberate ions. Ceramics International. 2012;38(5):3815-3820.
- 20. Yokoi T, Goto T, Kitaoka S. Formation of hydroxyapatite crystals from octacalcium phosphate with incorporated succinate ion under hydrothermal conditions. Chemistry Letters. 2019;48(8):855-885.
- 21. Koutsopoulos S. Synthesis and characterization of hydroxyapatite crystals: A review study on the analytical methods. Journal of Biomedical Materials Research: An Official Journal of the Society for Biomaterials, The Japanese Society for Biomaterials, and The Australian Society for Biomaterials, and the Korean Society for Biomaterials. 2002;62(4):600-12.
- 22. Stifler CA, Wittig NK, Sassi M, Sun CY, Marcus MA, Birkedal H, *et al.* X-Ray Linear Dichroism in Apatite. Journal of the American Chemical Society. 2018;140(37):11698-11704.
- 23. Mishra SP. Phase Transformation of organo-modifided plate-shaped OCP to Laminated HAP Nanocrystals. International Journal of Science and Research. 2020;10:292-294.
- 24. Mishra SP. Introductory of Scherrer's equation in laminated plate-shaped hexagonal hydroxyapatite Nano crystals System. Chemical Science International Journal. 2020;29:22-28.
- 25. Iijima M, Tohda H, Moriwaki Y. Growth and Structure of Lamellar mixed Crystals of Octacalcium Phosphate and Apatite in a Model System of Enamel Formation. Journal of Crystal Growth. 1992;116(3-4):319-326.
- 26. Jhan YH, Tseng JCC, Chan, Mou CY. Biomimetic formation of hydroxyapatite Nano rods by a single-crystal-to-single-crystal transformation. Advanced Functional Materials. 2005;15(12):2005-2010.